

Reaction sintered Al_2O_3 / Al_2TiO_5 microcrack-free composites obtained by colloidal filtration

S. Bueno, R. Moreno, C. Baudín

Instituto de Cerámica y Vidrio, C.S.I.C - Campus de Cantoblanco, Camino de
Valdelatas s/n, 28049 Madrid (Spain)

Abstract

Dense and microcrack-free Al_2O_3 / Al_2TiO_5 composites (10, 30 and 40 vol. % of Al_2TiO_5) have been obtained by colloidal filtration and reaction sintering, using alumina and titania as starting powders. The processing of the composites has been studied focusing on the rheological behaviour of aqueous suspensions of each powder and of mixtures. Colloidal filtration of optimised suspensions, with a solid loading as high as 50 vol. %, and a thermal treatment at 1450°C , lead to completely reacted and uncracked sintered materials with homogeneously distributed aluminium titanate contents up to 40 vol. % and high density. Thermal diffusivity values from 25 to 800°C are coincident on heating and cooling for the three studied composites, and decrease with temperature and with aluminium titanate content.

Keywords: Slip casting; Composites; Al_2O_3 ; Al_2TiO_5 ; Thermal conductivity

1. Introduction

Alumina (Al_2O_3)-aluminium titanate (Al_2TiO_5) composites can offer improved flaw tolerance and toughness¹⁻⁶. Aluminium titanate is highly anisotropic ($\alpha_{a25-1000^\circ\text{C}} = 10.9 \cdot 10^{-6} \text{ }^\circ\text{C}^{-1}$, $\alpha_{b25-1000^\circ\text{C}} = 20.5 \cdot 10^{-6} \text{ }^\circ\text{C}^{-1}$, $\alpha_{c25-1000^\circ\text{C}} = -2.7 \cdot 10^{-6} \text{ }^\circ\text{C}^{-1}$)⁷, therefore, even though the average crystallographic thermal expansion of aluminium titanate is slightly higher than that of alumina ($\alpha_{A25-1000^\circ\text{C}} = 8.7 \cdot 10^{-6} \text{ }^\circ\text{C}^{-1}$, $\alpha_{AT25-1000^\circ\text{C}} = 9.7 \cdot 10^{-6} \text{ }^\circ\text{C}^{-1}$)⁷⁻⁸, high compressive residual stresses on the aluminium titanate grains are expected to develop during cooling from the sintering temperature, at least for some grain-matrix crystallographic orientations. Consequently, Al_2TiO_5 grains may act as bridges during fracture. Moreover microcracking may also occur during fracture due to the residual stresses.

The characteristics of the toughness curve and, therefore, the flaw tolerance of alumina-aluminium titanate composites may be strongly modified by appropriately altering the microstructure. There is a range of volume fraction-particle size in which stable microcrack growth occurs during loading, leading to nonlinear stress-strain behaviour and to an enlargement of the range of crack sizes for which the material is flaw tolerant. Limits are imposed by the possible coalescence of multiple microcracks and, consequently, loss of strength^{6, 9}.

Moreover, due to the extreme local stresses that develop in alumina-aluminium titanate composites, spontaneous microcracking usually occurs during cooling from the sintering temperature and coalescence of these microcracks may even nucleate the failure of the unloaded material. In this sense, the microstructure of the materials has to be controlled to reach sufficient stress level to obtain the desired non-linear stress-strain

behaviour without generalised failure. In this sense, increasing contents of aluminium titanate particles of controlled size would improve the mechanical response of the composites.

Dense alumina–aluminium titanate composites with controlled microstructure have been fabricated from alumina and previously reacted aluminium titanate powders^{1-2, 5-6, 10}. Another way to fabricate such composites which, in principle, appears as more attractive in terms of energy saving, is by the reaction sintering of alumina and titania (TiO₂) mixtures^{3-4, 11}. Most resultant microstructures obtained by reaction sintering display low as-fired densities, abnormal grain growth and even unreacted titania particles, due to the special characteristics of the alumina-titania reaction process¹²⁻¹⁴. A previous work¹¹ reported that a careful control of processing green compacts made of alumina powders covered by a titania precursor allowed the attainment of high density (~98 % of theoretical) in alumina with up to 20 vol.% of aluminium titanate materials. However, composites with larger second phase contents (~20 – 40 vol. %) gave lower densities (~95 % of theoretical).

In this work, the possibility of obtaining completely reacted and dense alumina–aluminium titanate composites with controlled microstructure by reaction sintering of alumina and titania powders prepared by colloidal processing is investigated.

In order to achieve homogeneous microstructures with uniform distribution of the second phase and completely reacted aluminium titanate, a strict control of the colloidal properties of the mixture and the thermal treatment has to be accomplished. The colloidal behaviour of titania in water has been extensively studied¹⁵, as well as the stability of moderately concentrated suspensions¹⁶. However, concentrated TiO₂ suspensions in water exhibit a marked adhesive character and stick to tools and

containers, thus impeding homogeneous mixing. As a consequence, concentrated TiO₂ suspensions display a strong dilatancy, which might be responsible for heterogeneity of the Al₂O₃ + TiO₂ compacts obtained previously with colloidal dispersion methods¹⁶. In this work, the dispersing conditions were optimised through rheological characterisation to obtain suspensions with high solids content (i.e. 50 vol. %) and low viscosity.

The sintering schedule was adjusted in order to achieve complete reaction and densification of the compacts avoiding extensive grain growth.

Many properties of microcracked materials present strong hysteresis while heating and cooling due to crack closure and healing at high temperatures and re-microcracking during cooling. In particular, a significant hysteresis effect on thermal diffusivity was reported for MgTi₂O₅ and Fe₂TiO₅ polycrystalline ceramics¹⁷⁻¹⁸. Hence, microstructural observations and the evolution of thermal diffusivity with temperature have been used to analyse the influence of the volume fraction of aluminium titanate on microcrack formation.

2. Experimental

Alumina based composites with 10, 30 and 40 vol. % of Al₂TiO₅, (A10AT, A30AT, and A40AT) were obtained by reaction sintering of green compacts prepared from mixtures of Al₂O₃ and TiO₂ with relative TiO₂ contents of 5, 15, and 20 wt. %. High purity commercial powders of α -Al₂O₃ (Condea, HPA05 without MgO, USA, d₅₀ = 0.35 μ m, specific surface area: 9.5 m²/g) and TiO₂ (Anatase, Merck, 808, Germany, d₅₀ = 0.35 μ m, specific surface area: 9 m²/g) were used.

Colloidal stability was determined through zeta potential measurements by microelectrophoresis (Zeta-Meter, 3.0+, USA) for TiO₂ and Al₂O₃ suspensions prepared to a solid loading of 0.01 wt. %; pH was adjusted by addition of either HCl or tetramethylammonium hydroxide (TMAH), and 10⁻² M KCl was used as inert electrolyte to control the ionic strength. A carbonic acid based polyelectrolyte (Dolapix CE64, Zschimmer-Schwarz, Germany) was used as the dispersing aid. The influence of the polyelectrolyte concentration on the zeta potential was also investigated.

Aqueous suspensions of each powder and their mixtures were prepared to a solid loading of 50 vol. % (80 wt. %) by ball milling, using alumina jar and balls. Dispersing conditions were optimised through rheological characterisation of TiO₂ suspensions as a function of dispersant concentration (0.1 – 1.0 wt. % on a dry solids basis) after 2 h ball milling; later, the effect of milling time was studied to determine the optimum dispersant proportion. Measurements of viscosity were performed with a rotational rheometer (Haake RS50, Germany). Flow curves of the suspensions were determined for a range of shear rates between 0 and 1000 s⁻¹ at a constant temperature of 25 °C. Measurements were also performed by operating under controlled stress conditions in order to determine the yield point from the log/log plot of shear stress versus deformation¹⁹.

The green compacts blocks, 70 x 70 x 12.5 mm³, were obtained by colloidal filtration on plaster of Paris moulds and dried in air. To obtain the materials the dried blocks were sintered in air in an electrical box furnace (Termiber, Spain) at heating and cooling rates of 2°Cmin⁻¹ and 2h dwell at the maximum temperature, 1450°C.

The densities of the green and sintered compacts were determined by the Archimedes method, using mercury and water, respectively. Theoretical densities were calculated

taking values of 3.99 g cm^{-3} for alumina²⁰, 3.89 g cm^{-3} for TiO_2 (anatase)²¹, 4.25 g cm^{-3} for TiO_2 (rutile)²² and 3.70 g cm^{-3} for aluminum titanate²³. The phases present were determined by X – ray diffraction after grinding (Siemens AG, D5000, Germany) and results were processed using the ASTM – Files²⁰⁻²³.

Microstructural characterisation was performed by scanning electron microscopy (SEM, Zeiss DSM 950, Germany) on polished and thermally etched ($1440^\circ\text{C} - 1\text{min}$) surfaces.

From the sintered blocks, thin discs (diameter = 12.7 mm, thickness = 1 mm) were machined and covered with graphite for thermal diffusivity measurements, which were carried out from room temperature up to 800°C , on heating and cooling, using the laser flash method (Holometrix ThermalFlash, USA).

3. Results

In Figure 1 the zeta potential curves as a function of pH are shown for aqueous suspensions of Al_2O_3 and TiO_2 , the isoelectric point occurring at pH values of about 9 and 4, respectively. Kosmulski¹⁵ has made an extensive review of the points of zero charge of TiO_2 , which range from 2 to 8.9, and the average value is 5.6. Lower values of the ZPC are attributed to the presence of residual phosphate or other anionic impurities in commercial Titania. High absolute values of the zeta potential ($> 20 \text{ mV}$) are only reached at very low or very high pH conditions ($\text{pH} < 3$ or $\text{pH} > 12$)

Figure 2 shows the variation of zeta potential as a function of the concentration of dispersant. The best values are found for additive contents of 0.5 and 0.8wt % for Al_2O_3 and TiO_2 suspensions, respectively.

The rheological behaviour of concentrated TiO_2 suspensions was initially studied as a function of the deflocculant content. The measured flow curves are shown in figure 3, where the lowest viscosity is found for a polyelectrolyte concentration of 0.5wt.%.

The effect of milling time on TiO_2 suspensions dispersed with 0.5wt.% of polyelectrolyte is observed in the flow curves plotted in figure 4. For given shear rates, the shear stress diminishes with milling time, but incipient thixotropic behaviour is observed for 6h and this effect increased for longer milling times. For suspensions ball milled for 1h and 24h, the torque of the rheometer was exceeded as a consequence of the strong stickiness of the suspensions, indicating an obvious lack of homogeneity.

Figure 5 plots the flow curves of Al_2O_3 and TiO_2 slurries as well as their mixtures. Suspensions with 5 and 15wt.% of TiO_2 are coincident (22Pa at 500s^{-1}). A strong difference between Al_2O_3 and TiO_2 aqueous suspensions is observed and the rheological behaviour of the mixture is governed by the major phase. Therefore, deleterious thixotropic effects of TiO_2 suspensions are avoided.

The relative densities of green and sintered samples are summarised in Table 1. The green density of samples obtained by slip casting from the optimised suspensions tends to slightly decrease for increasing TiO_2 content, although high values, above 62.5% of theoretical, are found in all cases. Sintered density diminishes with aluminium titanate content from ≈ 97.5 to $\approx 96.5\%$ of theoretical for the A40AT samples.

The X-ray diffraction profiles in figure 6 show the position of characteristic peaks for alumina and aluminium titanate, selected to study the presence of these phases in the three composites. In all cases, the rutile phase was not detected.

Microstructures of the sintered materials are shown in figure 7. Only alumina and aluminium titanate were observed by this method (SEM). In all samples, aluminium titanate is homogeneously distributed and located mainly at alumina triple points and grain boundaries. No intragranular porosity is observed in the alumina grains even in the samples with 10vol.% of aluminium titanate (Fig. 7.a, b) in which the grain size of alumina ($\approx 5\mu\text{m}$) is much larger than in the samples containing increased amounts of aluminium titanate (Fig. 7. c-f). No microcracks are observed in any of the samples.

In figure 8 the thermal diffusivity, determined on heating and cooling cycles of the alumina and the three composite materials, is plotted as a function of temperature. For the four studied materials, values on heating and cooling are coincident and decrease with temperature and with aluminium titanate content.

4. Discussion

From zeta potential vs pH curves (Fig 1), heterogeneous mixtures would be obtained at pH values ranging from 3 to 10, since the particle surfaces of the two powders are oppositely charged, thus leading to heterocoagulation. Hence, purely electrostatic stabilization is only possible at very aggressive pH conditions. Consequently, the use of a polyelectrolyte capable of providing an electrostatic stabilizing mechanism was chosen in order to achieve a good dispersion of the mixtures.

From Fig. 2, well-dispersed mixtures of Al_2O_3 and TiO_2 will be obtained for polyelectrolyte contents larger than 0.5wt.%. Since Al_2O_3 is the major component of all the compositions studied, a content of 0.5wt.% of dispersant, coincident with the maximum zeta potential of Al_2O_3 , was selected.

The flow curves of TiO_2 slips, ball-milled for 2h, show a lower viscosity for a dispersant content of 0.5wt.%, in good agreement with the zeta potential measurements. A higher dispersant content makes for an increased viscosity and leads to Bingham plastic behaviour.

From Fig. 4 the critical influence of milling time on viscosity is obvious. The concentrated TiO_2 slips have a marked sticky character that restricts the effective milling time to a narrow range of times from 2 to 6h. However, for 6h milling some thixotropy develops thus impeding stability over time. In addition, the preparation of the TiO_2 /water mixture previous to ball milling was also critical. The powder added to water was first mechanically stirred at different rates. Below 800 rpm the powder stuck to the propeller leading to agglomeration. Above 1000 rpm the suspension became strongly dilatant and no effective mixing was reached. Homogeneous slurries could only be prepared by repeated additions of small amounts of TiO_2 powder into the water containing the dispersant stirred at 900 rpm.

The large differences between Al_2O_3 and TiO_2 aqueous suspensions, with the same solids loading, are evident in Fig. 5. The viscosity of the mixtures is controlled by the major phase (Al_2O_3) although the addition of TiO_2 increases the viscosity and incipient thixotropic behaviour arises for the highest TiO_2 content. However, the viscosity remains low enough to allow the slip to be cast easily. Viscosity values of 43, 44 and 51 mPa·s were obtained at a shear rate of 500 s^{-1} for mixtures with 5, 15 and 20 wt. % of

TiO₂ respectively. Measurements performed under CS (control stress) conditions confirmed the evolution toward plasticity of the mixtures with higher titania contents, with a yield point of more than 1Pa for the TiO₂ suspension (Table 2). These values are very low considering the high solid loadings (50vol.%) of the suspensions. The optimised dispersing conditions (4h ball milling and 0.5wt.% of dispersant) led to high green density bodies, a consequence of the good stability and homogeneity of the mixtures (Table 1)

The optimised green processing conditions and the thermal treatment at a rather low temperature (1450°C) led to completely reacted and homogeneous sintered materials (Figs. 6 and 7) with no generalised cracking or microcracks at the SEM scale.

The thermal diffusivity of uncracked aluminium titanate materials is not known due to the difficulties associated with the preparation of dense and uncracked aluminium titanate bodies. Nevertheless, values should be in the range of those of other pseudobrookites, such as MgTi₂O₅ or Fe₂TiO₅, (0.009-0.010 cm²/s)¹⁷⁻¹⁸ which are about one order of magnitude lower than that of alumina (0.100 cm²/s, Fig. 8). As a consequence, the thermal diffusivity values decrease with aluminium titanate content (Fig. 8).

The temperature dependence of the thermal diffusivity of all materials on heating is typical of uncracked dielectric materials, in which diffusivity decreases with temperature, the opposite to materials in which crack healing at high temperatures (>500°C) leads to an increase of diffusivity¹⁷⁻¹⁸. This behaviour agrees with the absence of cracking observed by SEM (Fig 7) in the composites. Moreover, no differences are found between heating and cooling values for any of the four materials. This fact

demonstrates that no, or very little, cracking phenomena occurs in these materials thorough the whole thermal cycle¹⁷.

5. Conclusions

In this work, the processing parameters to obtain reaction sintered $\text{Al}_2\text{O}_3 - \text{Al}_2\text{TiO}_5$ composites from aqueous alumina and titania mixtures have been established.

Well-dispersed mixtures of Al_2O_3 and TiO_2 can be obtained by adding a polyelectrolyte, in amounts greater than 0.5wt.%. Mixtures with a solids loading of 50vol.% and without dilatancy can be prepared by strictly controlling the mixing energy and the milling time to get the viscosity of the mixtures controlled by the major phase (Al_2O_3).

Colloidal filtration of optimised suspensions and a thermal treatment at 1450°C, lead to completely reacted, dense (96.5-98% of theoretical density) and uncracked sintered materials with homogeneously distributed aluminium titanate contents up to 40vol.%.

Thermal diffusivity values at temperatures from 25 to 800°C are coincident on heating and cooling, decrease with aluminium titanate content and the temperature dependence is typical of uncracked dielectric materials.

Acknowledgements

This work was supported by the project CICYT MAT 2000-0949 and by the grant CSIC I3P-BPD2001-1 (Spain)

References

1. Runyan, J. L., Bennison, S. J., Fabrication of flaw-tolerant aluminum-titanate-reinforced alumina. *J. Eur. Ceram. Soc.*, 1991, **7**, 93-99.
2. Padture, N. P., Bennison, S. J., Chan, H. M., Flaw-tolerance and crack-resistance properties of alumina-aluminium titanate composites with tailored microstructures. *J. Am. Ceram. Soc.*, 1993, **76**, 2312-2320.
3. Bartolomé, J., Requena, J., Moya, J. S., Li, M., Guiu, F., Cyclic fatigue crack growth resistance of Al_2O_3 - Al_2TiO_5 composites. *Acta Mater.*, 1996, **44**, 1361-1370.
4. Bartolomé, J., Requena, J., Moya, J. S., Li, M., Guiu, F., Cyclic fatigue of Al_2O_3 – Al_2TiO_5 composites in direct push-pull. *Fatigue Fract. Engng. Mater. Struct.*, 1997, **20**, 789-798.
5. Uribe, R., Baudín, C., Influence of a dispersion of aluminum titanate particles of controlled size on the thermal shock resistance of alumina. *J. Am. Ceram. Soc.*, 2003, **86**, 846-850.
6. Padture, N. P., Runyan, J. L., Bennison, S. J., Braun, L. M., Lawn, B. R., Model for toughness curves in two-phase ceramics: II, Microstructural variables. *J. Am. Ceram. Soc.*, 1993, **76**, 2241-2247.

7. Taylor, D., Thermal expansion data. XI. Complex oxides, A_2BO_5 , and the garnets. *Brit. Cer. Trans. J.*, 1987, **86**, 1-6.
8. Taylor, D., Thermal expansion data: III. Sesquioxides, M_2O_3 with the corundum and the A-, B- and C- M_2O_3 . *Brit. Ceram. Trans. J.*, 1984, **83**, 92-98.
9. Lawn, B. R., Padture, N. P., Braun, L. M., Bennison, S. J., Model for toughness curves in two-phase ceramics: I, Basic fracture mechanics. *J. Am. Ceram. Soc.*, 1993, **76**, 2235-2240
10. Ananthakumar, S., Warriar, K. G. K., Extrusion characteristics of alumina-aluminium titanate composite using boehmite as a reactive binder. *J. Eur. Ceram. Soc.*, 2001, **21**, 71-78.
11. Okamura, H., Barringer, E. A., Bowen, H. K., Preparation and sintering of narrow-sized Al_2O_3 - TiO_2 composite powders. *J. Mater. Sci.*, 1989, **24**, 1867 – 1880.
12. Thomas, H. A. J., Stevens. R., Microstructure development during the reaction sintering of alumina and titania to produce aluminium titanate. p. 117-122 in *Br. Ceram. Proc.* N° 42. Ed. R. Stevens, D. Taylor, Stoke-on Trent, UK, 1989.
13. Freudenberg, B., Mocellin, A., Aluminium titanate formation by solid-state reaction of fine Al_2O_3 and TiO_2 powders. *J. Am. Ceram. Soc.*, 1987, **70**, 33-38.
14. Uribe, R., Baudín, C., Formación de titanato de aluminio por reacción en estado sólido de alúmina y titania. *Bol. Soc. Esp. Ceram. Vidr.*, 2000, **39**, 1-10.
15. Kosmulski, M., The significance of the difference in the point of zero charge between rutile and anatase. *Adv. Colloid Interface Sci.*, 2002, **99**, 255-264.
16. Requena, J., Moya, J. S., Pena, P., Al_2TiO_5 - Al_2O_3 functionally gradient materials obtained by sequential slip casting. *Ceram. Trans.*, 1992, **34**, 203-210

17. Siebeneck, H. J., Hasselman, D. P. H., Cleveland, J. J., Bradt R. C., Effect of grain size and microcracking on the thermal diffusivity of MgTi_2O_5 . *J. Am. Ceram. Soc.*, 1977, **60**, 336-338.
18. Siebeneck, H. J., Hasselman, D. P. H., Cleveland, J. J., Bradt R. C., Effect of microcracking on the thermal diffusivity of Fe_2TiO_5 . *J. Am. Ceram. Soc.*, 1976, **59**, 241-244.
19. Gutiérrez, C., Sánchez-Herencia, A. J., Moreno, R., ¿Plástico o pseudoplástico?. Métodos de determinación y análisis del punto de fluidez de suspensiones cerámicas. *Bol. Soc. Esp. Ceram. Vidr.*, 2000, **39**, 105-117.
20. ASTM File 42-1468. Database PDF (Power Diffraction File)
21. ASTM File 21-1272. Database PDF (Power Diffraction File)
22. ASTM File 21-1276. Database PDF (Power Diffraction File)
23. ASTM File 26-0040. Database PDF (Power Diffraction File)

Table 1

Relative density of green samples and specimens sintered at 1450 °C

	A	A10AT	A30AT	A40AT	T
Green	64.1 ± 0.5	63.9 ± 0.3	63.4 ± 0.5	62.5 ± 0.2	59.2 ± 0.1
1450 °C – 2 h	98.2 ± 0.1	97.4 ± 0.3	97.7 ± 0.5	96.5 ± 0.4	-

Table 2

Viscosity at 500 s⁻¹ and yield stress of Al₂O₃ – TiO₂ slips with 0.5 wt. % of deflocculant after 4 h milling (A: alumina; T: titania)

	Viscosity (mPa·s)	Yield Stress (Pa)
A	34	-
A + 5 wt. % T	43	0.16
A + 15 wt. % T	44	0.25
A + 20 wt. % T	51	0.26
T	142	1.18

Figure Captions

Fig. 1. Zeta potential of alumina (A) and titania (T) as a function of pH

Fig. 2. Zeta potential of alumina (A) and titania (T) with different deflocculant contents

Fig. 3. Flow curve of TiO₂ suspensions with different deflocculant contents after 2 h ball milling

Fig. 4. Flow curve of TiO₂ suspensions after different milling times with 0.5 wt. % of deflocculant content

Fig. 5. Flow curve of Al₂O₃ – TiO₂ aqueous suspensions after 4 h milling with 0.5 wt. % of deflocculant (A: Alumina; T:titania)

Fig. 6. XRD patterns of composites sintered at 1450 °C – 2 h with different aluminium titanate contents (A: α -Al₂O₃; AT: β -Al₂TiO₅; T: TiO₂-rutile)

Fig. 7. Scanning electron micrographs of polished and thermally etched (1440 °C – 1 min) surfaces of the studied materials A10AT (a, b), A30AT (c, d) and A40AT (e, f) Al₂O₃ grains appear with dark gray colour, Al₂TiO₅ of an intermediate gray shade, whereas TiO₂ would appear white and is not observed.

Fig. 8. Diffusivity values during heating and cooling for different aluminium titanate contents (open symbols mean cooling)